

# Hydrotech Coating Systems

## Dura-Systems Specification Advisory

Hydrotech Coating Systems  
13 Sloop Road  
Grand Isle, VT 05458  
Phone: (802) 318-1808  
Fax: (802) 372-4043  
[davedaigle@verizon.net](mailto:davedaigle@verizon.net)  
[www.hydrotechcoatingsystems.com](http://www.hydrotechcoatingsystems.com)

### **DURA-LASTIC ACCELERATOR & DURA-FLEX ACCELERATOR**

#### **Optional Accelerator for DURA-LASTIC:**

The final curing rate for the mixed and applied DURA-LASTIC may be speeded up with the use of the optional accelerator.

There may be times when it becomes important to expedite the final curing rate of an applied DURALASTIC Membrane System, such as when early access must be accommodated or in cooler application temperatures (70 degrees and under) when all coatings take longer to set up. By using the Accelerator, the working and application time is shortened by a small amount but the final cure time is substantially shortened by about one-third to one-half the normal set-up time.

The DURA-LASTIC Accelerator is available in 1-ounce vials and in one-quart cans. The Accelerator is tinted green for identification purposes. Depending on site temperature conditions up to three 1-ounce vials may be added to a 5-gallon pail of DURA-LASTIC for maximum effect.

#### **Optional Accelerator for DURA-FLEX:**

DURA-FLEX Urethane is moisture cured and derives their drying action by drawing moisture only from the air. (Unlike the DURA-LASTIC, water is never added to DURA-FLEX!)

The optional DURA-FLEX Accelerator will aid to accelerate its ability to pull curing moisture out of the air at a faster rate than un-accelerated material. The additional cost of the Accelerator is often off-set by the ability to open up a coated area quicker.